

<b>KoMitsuLite Resin</b>			
<b>Density (g/cm<sup>3</sup>)</b>		2.88	
<b>Surface Tension (mN/m)</b>		8.90	
<b>Dynamic Viscosity (Pa*s)</b>			
<b>Temperature (°C)</b>	<b>3 rpm</b>	<b>6 rpm</b>	<b>12 rpm</b>
20	46.15	35.11	26.96
40	37.40	26.30	18.60
60	30.12	19.43	13.58

<b>KoMitsuLite Green</b>	
<b>Density (g/cm<sup>3</sup>)</b>	3.69

<b>KoMitsuLite Sintered</b>	
<b>Density (g/cm<sup>3</sup>)</b>	3.82
<b>Porosity (SEM)</b>	0.83%
<b>Water Absorbtion</b>	12.60%
<b>Flexural Strength (MPa)</b>	123.99
<b>Compressive Strength (MPa)*</b>	>314.301
<b>Hardness (GPa)</b>	18.25
<b>Specific Heat (J/g*K) 100C</b>	0.8
<b>Coefficient of Thermal Expansion</b>	2.3
<b>Percent Shrinkage @ 1700C</b>	
<b>X</b>	9.73
<b>Y</b>	10.14
<b>Z</b>	8.96
<b>Average</b>	9.61

\*Samples maxed out Tethon 3D testing equipment without failure